

## T-30

Rely® T-30 is designed the heavy duty applications where extreme heat and load conditions are factors.

### TYPICAL CHEMICAL PROPERTIES

		A-Side	B-Side
VISCOSITY	cps @ 77°F	1500	800
SPECIFIC GRAVITY	@ 77°F	1.05	1.04
MIX RATIO	By volume	1	1
	By weight	1.00	1.00
POT LIFE	Minutes @ 77°F 70,000 cps	35-65	
SHELF LIFE	Unopened	1 year	

### PHYSICAL PROPERTY DATA\*

		ASTM Method	Typical Result
SHORE A	Hardness	D2240	28
SPECIFIC GRAVITY		D792	1.05
TENSILE STRENGTH	psi	D412	195
ELONGATION AT BREAK	%	D412	480
	100% modulus	D412	110
	300% modulus	D412	215
TEAR STRENGTH	Die C, pli	D624	78
	Split Tear	D1938	13
REBOUND	%	D2632	59
COMPRESSION SET	%	D395	4

\* Physical Property Data obtained from product cured at 77°F for 16 hours and 24 hours at 150°F. Samples aged 7 days at 75°F before testing.

STORAGE CONDITIONS: Do not Expose to temperatures higher than 40°C (105°F). Keep in a dry place, tightly sealed.

### TYPICAL APPLICATION

Underground Mining Equipment  
Straddle Carriers  
High Reaching Scissor-lifts  
Aerial Booms  
Gantry Cranes  
Large Forklifts  
Scoops  
Scalers  
Earthmovers

Carpenter Co.  
Corporate Headquarters  
5016 Monument Avenue  
Richmond, Virginia  
[www.carpenter.com](http://www.carpenter.com)

**Customer Service  
General Information  
Orders  
800-825-6836  
866-290-7359**